

ARCHITECTURAL  
COMMERCIAL  
INDUSTRIAL  
PANEL

EXPOSED  
FASTENED


36"  
COVERAGE

WALL  
PANEL

OPEN FRAMING OR  
SOLID SUBSTRATE

### PANEL OVERVIEW


- Finishes: PVDF, MS Colorfast45® and Acrylic-Coated Galvalume®
- Corrosion Protection: AZ55 per ASTM A 792 for unpainted Galvalume®  
AZ50 per ASTM A 792 for painted Galvalume®  
G90 per ASTM A 653 for Galvanized
- Gauges: 26 ga and 24 ga standard; 22 ga optional
- 36" panel coverage, 1 1/4" rib height
- Panel Length: Minimum: 5'; Maximum: 45' recommended
- Exposed fastened metal building wall system
- Panels can be installed horizontally or vertically
- Trapezoidal rib on 12" centers



### TESTING AND APPROVALS


- UL 2218 Impact Resistance - Class 4
- UL 790 Fire Resistance Rating - Class A, per building code
- UL 263 Fire Resistance Rating - per assembly
- UL 580 Uplift Resistance - Class 90 Construction: #161
- Texas Windstorm - Evaluations RC-198 and RC-279
- 2023 FBC Approvals - FL9482.4, FL14645.11 and FL46539.3
- Miami-Dade County, Florida NOA 23-1214.04 - Wall expires 4/22/2030
- ICC Evaluation Report - ESR-2385

### ATTACHMENT DETAIL



### FASTENING PATTERNS

#### End of Panel



#### Field of Panel



### FASTENER INFORMATION

Overdriven fasteners will cause panel distortions.

Fasteners should extend 1/2" or more past the inside face of the support material.

Thick panels (ex. 18 ga) or supports (ex. 1/2" steel) may require predrilling of holes for screws.

#### Panel Fastener:

Attaching to Wood:  
#10-14 XL Wood Screw

#### Attaching to Steel:

#12-14 XL Self Drilling Screw

#### Trim Fastener:

1/4"-14 x 7/8" XL Stitch Screw

SECTION PROPERTIES					ALLOWABLE UNIFORM LIVE LOADS, psf For various fastener spacings														
Ga	Width in	Yield ksi	Weight psf	Top in Compression		Bottom in Compression		Inward Load						Outward Load					
				I <sub>xx</sub> in <sup>4</sup> /ft	S <sub>xx</sub> in <sup>3</sup> /ft	I <sub>xx</sub> in <sup>4</sup> /ft	S <sub>xx</sub> in <sup>3</sup> /ft	2'	3'	4'	5'	6'	7'	2'	3'	4'	5'	6'	7'
26	36	80	0.80	0.0357	0.0357	0.0303	0.0448	245	123	73	48	34	23	211	102	60	39	27	20
24	36	50	1.05	0.0543	0.0560	0.0437	0.0600	317	149	85	55	38	28	299	140	80	52	36	26
22	36	50	1.38	0.0780	0.0822	0.0613	0.0798	437	201	115	74	51	38	448	207	118	76	53	39

- Theoretical section properties have been calculated per AISI 2016 'North American Specification for the Design of Cold-Formed Steel Structural Members'. I<sub>xx</sub> and S<sub>xx</sub> are effective section properties for deflection and bending.
- Allowable load is calculated in accordance with AISI 2016 specifications considering bending, shear, combined bending and shear and deflection. Allowable load considers the 3 or more equal spans condition. Allowable load does not address web crippling, fasteners, support material or load testing. Panel weight is not considered.
- Deflection consideration is limited by a maximum deflection ratio of L/180 of span.
- Allowable loads do not include a 1/3 stress increase for wind.